

DENTAL Nice MATERIAL LIST

Email: info@dentalnice.com

web: www.dentalnice.com

Type	Name	Manufacture	Origin	CE #	LOT#	Composition
Vita ceramic powder	VMK-95	vita	Germany	0124	75280	
E-max ceramic powder	Emax Ceram 3	IVOCLAR Vivadent AG	Liechtenstein	0123	P62371	
Opaque Crystals	Ceramco 3	Dentsply	USA	0086		
WO Paste	Paste Wash Opaque	vita	Germany	0124		
OP Paste	paste Opaque	vita	Germany	0124		
Composite	solidex	SHOUFU	Janpan	00044		
Zirconia Blank	cerconbase	Degudent	Germany	0124		
	Emax press3	IVOCLAR Vivadent AG	Liechtenstein	0123		
	Zenotec color Zr	wieland	Germany	0483	160412	
	dental Zr Blank	UPCERA	China	EN45012	S2121155352	
Precious welding wire	standard S4 PF	Metalordental	Switzerland	1250		
red pencial lead	col-erase pencils	SANFORD	USA			
Non-precious alloy	Argeloy NP star	The Argen Corporation	USA			Ni61. 2%, Cr25. 8%, Mo11%Alx%, Si1. 5%, Cx%, Fex%
	Argeloy NP special	The Argen Corporation	USA		130147	co59. 5% cr. 31. 5%Si 2. 0% Mo 5. 0%
	Ceracast NNB	Mountain Medico, Inc	USA			cobalt 63% chromium 29% Molybdenum 6% silicon 1.1% Manganese 1. % Fe <1%

	starLoyc	Densply	Germany	0124		co. 59. 4% cr. 24. 5%w 10. 0% Si 1. 0% Mo 1. 0%
Cast partial alloy	vitallium 2000	Austenal	USA	0473	2074	cobalt60. 6% Molybdenum 6. 0%chromium 31. 5%
	wironit	Bego	Germany	0197	12989	Co 63% Cr 30% Mo 5% Si1. 1%
Titanium alloy	Tilite	Talladium Inc.	USA	0197	10611	
Silver palladium alloy	simidur S1S	wieland	Germany	0483		Pd 56% Ru 5% Ag 32% Sn 2% Ga 2% Zn 1%
Gold alloy	Solaro 3	Metalordental	Switzerland	1250		
High gold alloy	V-Gnathos pf	Metalordental	Switzerland	1250		AU. 86. 8% Pt. 11. 7% (1%)Ir. In. Fe. Mn. Ta
semi-precious alloy	V-Delta special	Metalordental	Switzerland	1250		Au 52. 5% Pd 25. 5% Ag 17% In 1% Sn 3. 5% (<1%) Ir. Ru. Cu. Zn
	paglin 2	Metalordental	Switzerland	1250		Au 3% Pd. 23% Ag 65% Cu 6. 5% In 2% (1%) Ir Zn
	ceradelta 2	Metalordental	Switzerland	1250		Pd 61. 5% Ag. 24. 5% In 2% Sn 10% Zn 2% (1%)Ru
	Argistar 43+(white)	The Argen Corporation	USA		6513031	Au 2. 0% Pd42. 9% Ag 46. 00% In 8. 00%
	Argenco 40 (yellow)	The Argen Corporation	USA		5526111	Au 40% Pd 19. 98% Ag20% In 17. 00 Zn 3. 0%
	Argedent Euro(white)	The Argen Corporation	USA		5379256	Au40% Pd39. 4% Ag10% In 8. 8% Ga1. 4%
Gold Alloy	Argedent 74 (yellow)	The Argen Corporation	USA	0086	5567209	Au74% Pd4% Ag7. 6% Ag10. 8% In 2. 5%
Acrylic teeth	cosmo/Excellence	Dentsply	USA	0088		
Acrylic	Lucitone 199	Dentsply	USA	0088		
Flexible Resin	Valplast	Valplast	USA	0510		
Othodontics	Thermoforming sheet	Erkodent	Germany		C12H1309SNa	
	Resin	Vertex	Netherlands			